

#### 

# **Rohs PVC Plastic Electrical Insulation Tape**



### SCOPE:

This specification covers RoHS PVC plastic electrical insulation tape to be used in electrical service at temperature  $0 \sim 80^{\circ}$  C. The tape shall be used for insulation of jointed splices of cables and wires. The tape must have good insulation properties, heat, weather, flame retardant and RoHS materials for environment, suitable for tropical country.

### **STANDARD:**

The RoHS PVC plastic electrical insulation tape shall be manufactured and tested in accordance with TIS 386-2531

## **Dimension**

1) Thickness (mm)  $0.125 \pm 0.025$ ,  $0.18 \pm 0.025$ 

2) Width (mm)  $19 \pm 1.0$ 3) Length (m) 10 + 1.0- 0

PROPERTY AND REQUIREMENTS	PACKING
1) Electrolytic corrosion after 24h	The RoHS PVC plastic electrical insulation tape
at 27 ± 2° Cand 93 ± 2% relative humidity $(\Omega) \ge 10^{11}$	shall be packing in paper core Cellophane and
2) Penetration at elevated temperature (°C) ≥ 50	shrinkage wrapped.
3) Flammability non-ignitable or	
self-extinguishing	1) Dimension of each roll
4) Thermal endurance no-crack	: Diameter (cm) 5.8
5) Tensile strength (N/10 mm width/mm thick.) ≥ 150	Width (cm) 1.9
6) Adhesion to steel (N/10 mm width/mm thick.) ≥ 1.8	2) Weight of each roll (approx.)
7) Adhesion to backing (N/10 mm width/mm thick.) ≥ 1.8	: Net (kg) 0.036
8) Shear adhesion after immersion in water (N) ≥ 18.0	Gross(kg) 0.037
9) Electric strength	3) Number of roll in each package (Rolls) 10
- after 24 hour at 27 ± 2° C	4) Number of package in one case (Package)10
and 65 ± 5% relative humidity (kV/mm) ≥ 40	5) Dimension of each case : WxLxH (cm) 12.5x30x19.5
- after 24 hour at 27 ± 2° C	6) Gross weight of each case (approx.) (kg) 4
and 93 ± 2% relative humidity (kV/mm) ≥ 35	